

REMARKS

The above amendments have been made to conform the claims to U.S. practice.


Respectfully submitted,

NATH & ASSOCIATES PLLC

Date: March 29, 2005

NATH & ASSOCIATES PLLC
1030 Fifteenth Street, N.W.
Sixth Floor
Washington, D.C. 20005-1503
GMN/GBK/ng: PrelimAmend

By:



Gary M. Nath
Registration No. 26,965
Gregory B. Kang
Registration No. 45,273
Customer No. 20529

Attachment A

1. (original) Shell for ballistic helmet formed from a plurality of paraaramide fabric layers and bonding resin, wherein said fabric layers have areal density equal or less than 200g/m^2 , said shell has average thickness less than 6.5 mm and average areal density less than 7.5 Kg/m^2 .
2. (original) Shell according to Claim 1, wherein at least one of said fabric layers has areal density less than 160g/m^2 .
3. (original) Shell according to Claim 1, wherein part of said fabric layers have areal density less than 160g/m^2 and the rest fabric layers have areal density between 200 and 160g/m^2 .
4. (original) Shell according to Claim 2, wherein part of said paraaramide fabric layers are KEVLAR-KM2®.
5. (original) Shell according to Claim 1, wherein said bonding resin constitutes less than 12% of the shell weight.
6. (original) Shell according to Claim 1, wherein said plurality of layers is greater than 28.
7. (original) Shell according to Claim 6, wherein said plurality of layers is not less than 33.
8. (original) Shell according to Claim 7, wherein said plurality of layers is not less than 38.
9. (original) Shell for ballistic helmet formed from a plurality of paraaramide fabric layers and bonding resin, wherein said plurality of layers is greater than 28 and said shell has average thickness less than 6.5 mm.
10. (original) Shell for ballistic helmet formed from a plurality of paraaramide fabric layers and bonding resin, wherein said plurality of layers is not less than 38.
11. (original) Shell for ballistic helmet formed from a plurality of paraaramide fabric layers and bonding resin, wherein

said fabric layers have areal density less than 200g/m^2 , and said plurality of layers is greater than 28.

12. (original) Shell for ballistic helmet formed from a plurality of paraaramide fabric layers and bonding resin, wherein said plurality of layers is greater than 28 and said shell has average areal density less than 7.0 Kg/m^2 .

13. (currently amended) Method for production of shell for ballistic helmet according to ~~anyone of the preceding claims~~ claim 12, including pressing and bonding of said plurality of layers at pressure equal or above 150Kg/cm^2 .

14. (original) Method according to Claim 12, wherein said pressure is equal or above 300Kg/cm^2 .